

Ancaster-Stretton Mixed Limestone

Ancaster-Stretton is mixed Limestone which is quarried and produced in Lincolnshire.



Technical Information (typical)

Description

Standard available course heights are: 65mm, 90mm, 115mm & 140mm. 215mm is also available in a limited format. Bed-width is 100mm (nominal) and lengths are random. Larger bed sizes and different course heights available on request. In addition, a full range of Masonry items are able to be offered.

Apparent Density

2379 / 2349/m³ to BS EN 1936 : 2006

Crushing Strength

47.94 / 51.9 Mpa

Water Absorption

4.27 / 4.84%

Porosity

12.06 / 12.82%

Saturation Coefficient

0.84 / 0.89

Northern Office

Lower Wharfe House, Wharfebank Mills
Ilkley Road, Otley, West Yorkshire LS21 3JP
Telephone: 01924 241100

Midlands and Southern Office

1 Hill House, Regent Street
Lutterworth, Leicestershire LE17 4BE
Telephone: 01455 559474

www.bbsnaturalstone.com
E: sales@bbsbrickandstone.co.uk