

# Stretton Limestone

Stretton Limestone is quarried and produced in Lincolnshire.



## Technical Information (typical)

### Description

Standard available course heights are: 65mm, 90mm, 115mm & 140mm. 215mm is also available in a limited format. Bed-width is 100mm (nominal) and lengths are random. Larger bed sizes and different course heights available on request. In addition, a full range of Masonry items are able to be offered.

<b>Apparent Density</b>	2349 kg/m <sup>3</sup>
<b>Crushing Strength</b>	51.9 Mpa
<b>Water Absorption</b>	4.84%
<b>Porosity [% by Vol]</b>	12.82%
<b>Saturation Coefficient</b>	0.89

### Northern Office

Lower Wharfe House, Wharfebank Mills  
Ilkley Road, Otley, West Yorkshire LS21 3JP  
Telephone: 01924 241100

### Midlands and Southern Office

1 Hill House, Regent Street  
Lutterworth, Leicestershire LE17 4BE  
Telephone: 01455 559474

[www.bbsnaturalstone.com](http://www.bbsnaturalstone.com)  
E: [sales@bbsbrickandstone.co.uk](mailto:sales@bbsbrickandstone.co.uk)