

CHATBURN SANDSTONE



PRODUCT DESCRIPTION

Appearance	Light buff with swirls of golden brown & orange
Petrographic Description	Hard-wearing medium to coarse grained millstone grit
Quarry Location	Lancashire
Available Finishes	Sawn, Sandblasted
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2320 KG/m ³	BS EN 1936 : 2006
Compressive Strength	84 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 5.8 MPa	BS EN 12372 : 2006
Water Absorption	39.5g/m2/sec2	BS EN 13755 : 2008
Slip Resistance	100 DRY 88 WET	BS EN14231 : 2003

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.