

Sunrise



Bush Hammered Finish

Description

Appearance:	Medium to coarse grained crystalline rock
Finishes:	Flamed, Fine Picked, Polished, Honed
Governing Standards:	Where applicable BS EN 1341/1342/1343 will be applied
Quarry of Origin:	Fujian, P.R.C

Physical Properties

Work Dimensions:	To Customer's specification
Tolerances on Dimensions:	Class 2
Compressive Strength:	178MPa
Abrasion Resistance:	18mm
Flexural Strength:	15MPa
Material Density:	2650kg/m ³ (typically)
Slip Resistance:	75 - WET (Flamed) 82 - DRY (Flamed)
Water Absorption:	0.5%

Supply

Crate Size:	Maximum 1.8 tonnes, approximate size 1.0 x 1.0 x 0.80 high
Packaging:	Wooden crates, suitable for stacking & transportation by forklift

Cleaning & Maintenance

All stones vary and each one should be looked at on an individual basis. Many are slightly alkali so acid cleaners should be avoided. For more information, please contact our technical department.