

Azul Leon



PRODUCT DESCRIPTION

Appearance	Grey colour rock with medium coarse grain
Petrographic Description	Calcarene Limestone
Quarry Location	Alicante, Spain
Available Finishes	Sawn, Honed
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2260 KG/m ³	BS EN 1936 : 2006
Flexural Strength	Under Concentrated Load: 12.2 MPa	BS EN 12372 : 2006
	After Freeze/Thaw Test (84 Cycles): 11.5 MPa	BS EN 12372 : 2006
Abrasion Resistance	25.5mm	BS EN 14157 : 2017
Water Absorption	5.6%	BS EN 13364 : 2008
Slip Resistance	98 DRY (Polished Finish)	BS EN 14231 : 2003
	62 WET (Polished Finish)	

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.