

Noturno Lucha



PRODUCT DESCRIPTION

Appearance	Grey rock with medium grain & granitic texture
Petrographic Description	Diorite
Origin	Spain
Available Finishes	Sawn, Flamed, Fine Picked, Polished, Honed
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2800 KG/m ³	BS EN 1936 : 2006
Compressive Strength	177 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 23.6 MPa	BS EN 12372 : 2006
Abrasion Resistance	17.5mm	BS EN 14157 : 2017
Water Absorption	0.1%	BS EN 13364 : 2008
Slip Resistance	87 DRY (Fine Picked Finish)	BS EN 14231 : 2003
	73 WET (Fine Picked Finish)	

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.