

Tarrenga Buff



PRODUCT DESCRIPTION

Appearance	Buff/Grey
Petrographic Description	Lithic Arenite Sandstone in accordance with BS EN 12407:2007
Origin	Lleida, Spain
Available Finishes	Sawn, Fine Picked, Honed
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2444 KG/m ³	BS EN 1936 : 2006
Compressive Strength	81.6 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 8.25 MPa	BS EN 12372 : 2006
Abrasion Resistance	23.8mm	BS EN 14157 : 2017
Water Absorption	2.8%	BS EN 13364 : 2008
Slip Resistance	88 DRY (Sawn Finish)	BS EN 14231 : 2003
	68 WET (Sawn Finish)	

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.