

Verdant Haze



PRODUCT DESCRIPTION

Appearance	Green rock with granitic texture
Petrographic Description	Granite
Quarry Location	Turkey
Available Finishes	Sawn, Fine Picked, Flamed
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	3002 kg/m ³	BS EN 1936 : 2006
Open Porosity	0.165%	BS EN 1936 : 2006
Compressive Strength	1643 kg/cm ²	BS EN 1926 : 2006
Abrasion Resistance	1.52mm	BS EN 14157 : 2017
Water Absorption	0.55%	BS EN 13755 : 2008

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.