

New Riven Yorkstone



PRODUCT DESCRIPTION

Appearance	Fine to medium grained sandstone
Petrographic Description	Sandstone
Quarry Location	Yorkshire, UK
Available Finishes	Natural Riven
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2430 KG/m ³	BS EN 1936 : 2006
Compressive Strength	132 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 18.9 MPa	BS EN 12372 : 2006
Abrasion Resistance	19.53 mm	BS EN 14157 : 2017
Water Absorption	2.4%	BS EN 13364 : 2008
Open Porosity	8.57%	BS EN 1936: 2006
Acid Immersion	Pass	BR 141

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.