

Westfield Buff Multi



PRODUCT DESCRIPTION

Appearance	Hard, fine grained sandstone
Petrographic Description	Sandstone
Quarry Location	West Yorkshire, UK
Available Finishes	Sawn
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2437 KG/m ³	BS EN 1936 : 2006
Compressive Strength	139 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 16.4 MPa	BS EN 12372 : 2006
Abrasion Resistance	N/A mm	BS EN 14157 : 2017
Water Absorption	2.4%	BS EN 13364 : 2008
Slip Resistance	N/A DRY (Sawn Finish)	BS EN 14231 : 2003
	74 WET (Sawn Finish)	
LRV Value	29.26 (Sawn Finish)	
Carbon Data	46.98kgs CO2e/m2 (delivered into London)	

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.